

Belzona 4331

FN10085

(MAGMA CR3)



INSTRUCTIONS FOR USE

1. TO ENSURE AN EFFECTIVE MOLECULAR WELD

APPLY ONLY TO CLEAN, FIRM, DRY AND WELL ROUGHENED SURFACES

a) SURFACE PREPARATION

(i) Concrete Surfaces

Remove all paint, tar and other coatings, as well as any loose surface material, before application of **Belzona® 4911**.

Horizontal concrete surfaces, as well as new concrete, will exhibit the phenomenon of laitance which must be removed prior to application. Allow new concrete to cure for a minimum of 28 days. Floors should have an effective vapor barrier installed.

Test for presence of moisture either

- In accordance with ASTM D4263 – plastic sheet method, or
- Measure moisture content using Electronic Moisture Meter <6% moisture (<15%WME)

If test is positive for presence of moisture, test further by either

- Measure Moisture Vapor Emission Rate in accordance with ASTM F 1869 - Anhydrous Calcium Chloride test. Acceptable if <3lbs/1000ft²/24 hours (15g/m²/24 hours), or
- Measure Relative Humidity of concrete in accordance with ASTM F2170. Acceptable if <75%

Once existing concrete surfaces have been prepared in accordance with these recommendations, proceed to Section 1 (b) "Conditioning".

NOTE:

All porous surfaces such as concrete require to be Conditioned with **Belzona® 4911** (Magma TX Conditioner).

(ii) Metallic surfaces

Remove all paint, tar and any other coatings.

Blast clean the metal surface to achieve the following standard of cleanliness:

ISO 8501-1 Sa 2½ very thorough blast cleaning.

American Standard near white finish SSPC SP 10.

Swedish Standard Sa 2½ SIS 05 5900.

Minimum depth profile should be 3 mils (75 microns). Now proceed to Section 3 "Combining the Reactive Components".

(iii) Areas already treated with **Belzona® 4111** (Magma Quartz).

Belzona® 4331 may be applied directly to **Belzona® 4111** without conditioning so long as the application takes place within 6 hours and the **Belzona® 4111** has been kept uncontaminated by foreign matter. In this case, proceed directly to Section 3 "Combining the Reactive Components". Where an existing **Belzona® 4111** application has been in service for longer than 6 hours, thoroughly clean and roughen the surface and then proceed to Section 3 "Combining the Reactive Components".

b) CONDITIONING

Add the entire contents of **Belzona® 4911** (Magma TX Conditioner) Solidifier to **Belzona® 4911** Base and stir thoroughly until completely mixed. Immediately brush conditioner onto the surface to be treated with **Belzona® 4331** not exceeding an area of 12 sq.ft. (1.1 sq.m) per 450g unit. Brush the **Belzona® 4911** well into the surface using a stiff bristled brush.

Conditioning and overcoating must be complete within the times shown.

Temperature	Usable life after mixing	Minimum Overcoating	Maximum Overcoating*
59°F/15°C	55 mins	Application can commence as soon as conditioning has been completed.	6 hours
68°F/20°C	45 mins		6 hours
77°F/25°C	32 mins		6 hours
86°F/30°C	20 mins		6 hours

*If the maximum overcoating time for the **Belzona® 4911** is exceeded, then the cured surface should be abraded and fresh **Belzona® 4911** applied.

2. STORAGE

Store in a dry environment at a temperature between 59°F (15°C) and 86°F (30°C).

Inadvertent storage of **Belzona® 4331** Solidifier below 59°F (15°C) can result in partial solidification. If this occurs, the material can be restored to its normal form by resealing the container and warming to 104°F (40°C) in a well ventilated dry area.

Check that the Solidifier is a clear mobile liquid immediately before use.

3. COMBINING THE REACTIVE COMPONENTS

Add the entire contents of **Belzona® 4331** Solidifier to **Belzona® 4331** Base. Mix thoroughly until a complete homogeneous liquid free from any streaks is achieved.

NOTES:

1. MIXING AT LOW TEMPERATURES

To ease mixing when the material temperature is below 59°F (15°C), warm the Base and Solidifier modules until the contents attain a temperature of 68-77°F (20-25°C).

2. WORKING LIFE

From the commencement of mixing, **Belzona® 4331** must be used within the times shown below.

Temperature	59°F/15°C	68°F/20°C	86°F/30°C
Use all material within	45 mins	20 mins	15 mins

3. MIXING SMALL QUANTITIES

For mixing small quantities of **Belzona® 4331** use: 10.75 parts Base to 1 parts Solidifier by weight.

4. VOLUME CAPACITY OF MIXED **BELZONA® 4331**

60 cu.in. (975 cm³) per 1.5kg unit.

4. APPLYING **BELZONA® 4331**

FOR BEST RESULTS

Do not apply when:

- The temperature is below 59°F (15°C) or the relative humidity is above 90%.
- Rain, snow, fog or mist is present.
- There is moisture on the metal surface or is likely to be deposited by subsequent condensation.
- The working environment is likely to be contaminated by oil/grease from adjacent equipment or smoke from kerosene heaters or tobacco smoking.

APPLICATION LIMITS

Belzona® 4331 can be applied when the temperature is anywhere between 59°F and 86°F (15°C-30°C). Above 86°F (30°C) the material may be too "fluid" to enable the required thickness, or build up, to be obtained on vertical surfaces

COVERAGE RATES

Recommended number of coats	2	1
Target thickness 1 st coat	20 mils (500 microns)	20 mils (500 microns)
Target thickness 2 nd coat	20 mils (500 microns)	N/A
Maximum total DFT	Only limited by sag resistance	
Theoretical coverage rate 1 st coat	20.9 sq.ft/1.5kg unit (1.95m ² /1.5kg unit)	20.9 sq.ft/1.5kg unit (1.95 m ² /1.5kg unit)
Theoretical coverage rate 2 nd coat	20.9 sq.ft/1.5kg unit (1.95 m ² /1.5kg unit)	N/A
Theoretical coverage rate to achieve minimum recommended system thickness 16 mils (400 micron)	25.8 sq.ft/1.5kg unit (2.4 m ² /1.5kg unit)	25.8 sq.ft/1.5kg unit (2.4 m ² /1.5kg unit)

PRACTICAL COVERAGE RATES

Appropriate loss factors must be applied to the above coverage rates. In practice, many factors influence the actual coverage rate achieved. On rough surfaces such as pitted steel the practical coverage rate will be reduced. Application at low temperatures will also reduce practical coverage rates further.

4.1 APPLICATION AS A 1 COAT SYSTEM

Where application conditions permit, **Belzona® 4331** may be applied as a single coat.

Apply the **Belzona® 4331** directly on to the prepared surface with a stiff bristled brush or with the plastic applicator provided at the recommended coverage rate.

Application to rough or irregular surfaces may reduce this coverage by 20 - 25%.

TO ACHIEVE A UNIFORM COATING

- Apply the coating in one operation without interruption.
- Use a brush or applicator to initially wet out the substrate before building up to the full coating thickness.
- Use a wet film thickness gauge to regularly check that the correct film thickness is being achieved.
- Finish application with a brush to obtain uniform coverage.
- Pay careful attention to coating detail areas such as brackets, edges and corners.
- Ensure adequate lighting is available to prevent misses.

4.2 APPLICATION AS A 2 COAT SYSTEM

- Apply the first coat of **Belzona® 4331** as in 4.1 above, and allow to harden (use time to resist pedestrian traffic in section 5 as a guide).
- Before applying the second coat, wash the surface of the **Belzona® 4331** with a warm detergent solution to remove any amine bloom that has formed. Rinse with clean water and allow to dry.
- Carefully grit blast using a moderate blast pressure and fine grit to remove surface layer, but without significant loss of coating. A frosted appearance free from gloss should be produced with a target profile of 1.5 mil (40 microns). Remove debris and degrease

with **Belzona® 9111** or any other effective cleaner which does not leave a residue e.g. MEK. Allow solvent to evaporate.

- Apply a second coat of **Belzona® 4331**.

INSPECTION

- Immediately after application of each unit, visually inspect for pinholes and misses. Where detected these should be immediately brushed out.
- Once the application is complete and the coating has hardened, carry out a thorough visual inspection to confirm freedom from pinholes and misses, and to identify any possible mechanical damage.
- Spark testing in accordance with NACE SP0188 can be carried out to confirm coating continuity. A voltage of 3kV is recommended to confirm that a minimum coating thickness of 20 mil (500 microns) has been achieved.

REPAIRS

Any misses, pinholes or mechanical damage found in the coating should be repaired by grit blasting or abrading the surface to produce a frosted appearance free of gloss, prior to application of further material as detailed in 4.2 above.

CLEANING

Mixing tools should be cleaned immediately after use with **Belzona® 9111** or any other effective solvent e.g. Methyl ethyl ketone (MEK). Application tools should be cleaned using a suitable solvent such as **Belzona® 9121**, MEK, acetone or cellulose thinners.

5. COMPLETION OF THE MOLECULAR REACTION

Allow **Belzona® 4331** to solidify as below before subjecting it to the conditions indicated.

	Pedestrian traffic	Chemical resistance
59°F/15°C	12 hours	7 days
68°F/20°C	8 hours	5 days
86°F/30°C	4 hours	3 days

Below 59°F (15°C) solidification times will be significantly extended and the resultant chemical resistance capability of the **Belzona® 4331** will be reduced.

6. FORCE CURE FOR OPTIMUM CHEMICAL RESISTANCE

Allow **Belzona® 4331** to solidify for 12 hours at 68°F (20°C) then force cure the product at 180°F (80°C) for 4 hours, to attain maximum chemical resistance properties.

7. NON-SLIP SURFACE

Belzona® 4331 will solidify to a smooth, hard finish. As such for pedestrian traffic areas, it is strongly recommended that **Belzona® Grip Systems Aggregate** be broadcast into the **Belzona® 4331** immediately after application. The choice and amount of Aggregate will vary with the degree of non-slip desired. While personal safety will be enhanced, the ultimate chemical resistance of **Belzona® 4331** may be slightly reduced.

HEALTH & SAFETY INFORMATION

Please read and make sure you understand the relevant Safety Data Sheets.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2019 Belzona International Limited. Belzona® is a registered trademark.

*Belzona products are
manufactured under an
ISO 9001 Registered
Quality Management System*

